

ARMRNPRIM

ARMOR RENEW WOOD PRIMER

PRODUCT DESCRIPTION

Water-based acrylic coating designed for application on structurally sound wood surfaces. It is suitable for use on weathered, worn or previously coated wood decks, docks and exterior furniture.

Armor Renew Wood Primer can only be used under Armor Renew Wood and Concrete Resurfacer. Do not use under a transparent, semi-transparent, clear or penetrating deck coat. Not for use on composite decking, concrete, fiberglass, tile or metal surfaces. These surfaces will not allow for proper adhesion. Do not use on driveways, garages or other areas with vehicular traffic.

FOR EXTERIOR USE ONLY

PRODUCT FEATURES

- Used for priming on wood substrates
- No sanding or stripping required
- Works on weathered & worn wood
- Clean, prime & coat
- Used with Armor Renew Wood and Concrete Resurfacer (Smooth or Textured Version)
- Can be applied using a 3/8" nap roller, a short nap stain pad or a synthetic paint brush.

PRODUCTS TO BE USED WITH

- Renew Deck Cleaner
- Renew Wood and Concrete Resurfacer (Smooth or Textured)

PHYSICAL PROPERTIES

Resin Type	Water-based Acrylic
Pigment Type	None
Solvents	Glycol Ethers, Water
Weight-Per Gallon	8.6 lbs
Weight-Per Liter	1.03 kg
Solids By Weight	35.6%
Solids By Volume	33.5%
Volatile Organic Compounds	<750 g/l (0.62lbs./gal.)
Recommended Dry Film Thickness(DFT)/Coat	2 mils
Practical Coverage (assume 15% material loss)	Approximately 450-500 sq.ft./gal Rates will vary based on surface profile
Dry Times (@ 70-80°F (21-27°C) and 50% RH)	---
Touch	30 minutes
Recoat	1 Hour
Full Cure	7 days
Shelf Life	5 Years
Flash Point	>200°F (93°C)
Storage	Protect from freezing.
Safety Information	For additional information, see the SDS

BENEFITS



Ready for Topcoat in
1-2 hours



Works on
Wood surfaces



One Coat
System



No Sanding
Needed



Roll on
Application

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.